

03-06-00

A


FISH & RICHARDSON P.C.

4225 Executive Square
Suite 1400
La Jolla, California
92037

Telephone
858 678-5070

Facsimile
858 678-5099

Web Site
www.fr.com



Frederick P. Fish
1855-1930
W.K. Richardson
1859-1951

March 2, 2000

Attorney Docket No.: 07977/015003/US2954/2957D2

Box Patent Application

Assistant Commissioner for Patents
Washington, DC 20231

Presented for filing is a new continuation patent application of:

Applicant: SHUNPEI YAMAZAKI; YASUHIKO TAKEMURA; SETSUO
NAKAJIMA and YASUYUKI ARAI

Title: DISPLAY DEVICE AND METHOD OF FABRICATING THE
SAME

Enclosed are the following papers, including all those required to receive a filing date
under 37 CFR §1.53:

	Pages
Specification	21
Claims	10
Abstract	1
Declaration	2 (copy from parent)
Drawing(s)	5

CERTIFICATE OF MAILING BY EXPRESS MAIL

Express Mail Label No. EL 528 178 801 US

I hereby certify that this correspondence is being
deposited with the United States Postal Service as
Express Mail Post Office to Addressee with sufficient
postage on the date indicated below and is addressed to
the Assistant Commissioner for Patents, Washington,
D.C. 20231.

Date of Deposit

March 2, 2000

Signature

Typed or Printed Name of Person Signing Certificate

Deborah Dean

BOSTON
DELAWARE
NEW YORK
SILICON VALLEY
SOUTHERN CALIFORNIA
TWIN CITIES
WASHINGTON, DC

Box Patent Application

March 2, 2000

Page 2

Enclosures:

- Rule 63 declaration, copy from a previous application under rule 63(d) for continuation or divisional only.
- Information Disclosure Statement: Applicant calls attention to documents listed on attached form(s) PTO-892 and PTO-1449 from parent case(s). Per Rule 97(d) copies of those documents are not provided.
- Postcard.

This application is a continuation (and claims the benefit of priority under 35 USC §120) of U.S. application serial no. 09/062,873, filed April 20, 1998. The disclosure of the prior application is considered part of (and is incorporated by reference in) the disclosure of this application.

Preliminary Amendment:

Page 1 of the specification, before line 1, insert --This is a continuation of U.S. application serial no.09/062,873, filed April 20, 1998, (pending).--

The prior application is assigned of record to Semiconductor Energy Laboratory Co., Ltd., a Japanese corporation, by virtue of an assignment submitted to the Patent and Trademark Office for recording on March 8, 1996 at Reel 8068/Frame 0107.

Priority is claimed under 35 USC §119 based on priority applications serial number 7-86457 filed March 16, 1995 and serial number 7-79708 filed March 10, 1995 in Japan.

27 Total Claims; 6 independent

Basic filing fee	\$ 760.00
Total claims in excess of 20 times \$18.00	126.00
Independent claims in excess of 3 times \$78.00	234.00
Multiple dependent claims	0.00
Total filing fee:	\$1120.00


A check for the filing fee is enclosed. Please apply any other required fees or any credits to deposit account 06-1050, referencing the attorney docket number shown above.

[illegible]

Page 3

Kindly acknowledge receipt of this application by returning the enclosed postcard.

Scott C. Harris
Fish & Richardson P.C.
4350 La Jolla Village Drive
Suite 500
San Diego, CA 92122


Scott C.
Reg. No

Scott C. Harris
Reg. No. 32,030

Enclosures

10020962.doc

APPLICATION
FOR
UNITED STATES LETTERS PATENT

TITLE: DISPLAY DEVICE AND METHOD OF FABRICATING
THE SAME

APPLICANT: SHUNPEI YAMAZAKI, YASUHIKO TAKEMURA,
SETSUO NAKAJIMA AND YASUYUKI ARAI

CERTIFICATE OF MAILING BY EXPRESS MAIL

Express Mail Label No. EL 528 178 801 US

I hereby certify that this correspondence is being deposited with the United States Postal Service as Express Mail Post Office to Addressee with sufficient postage on the date indicated below and is addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

March 2, 2000
Date of Deposit

Signature

Deborah Dear
Typed or Printed Name of Person Signing Certificate

DISPLAY DEVICE AND METHOD OF FABRICATING THE SAME

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a passive matrix or active matrix display such as a liquid crystal display and, more particularly, to a fashionable display device in which the ratio of the area of the display portion to the area of the substrates of the display device is increased by effectively mounting a driver semiconductor integrated circuit.

2. Description of the Related Art

Passive matrix type and active matrix type constructions are known as matrix display devices. In the passive matrix type, a number of stripe-shaped conducting lines (row lines) made of a transparent conductive film or the like are arrayed in a certain direction on a first substrate. On a second substrate, similar stripe-shaped conducting lines (column lines) are arrayed in a direction substantially perpendicular to the conducting lines on the first substrate. Both substrates are so arranged that the conducting lines on them intersect each other.

An electrooptical material such as a liquid crystal material whose transparency, reflectivity, or scattering performance is varied by a voltage, current, or the like is positioned between both substrates. If a voltage or current is applied between an addressed row line on the first substrate and an addressed column line on the second substrate, then the transparency, reflectivity, or scattering performance at the intersection can be set to a

desired value. In this way, the display device can be matrix driven.

In the active matrix construction, row and column lines are formed on the first substrate by multilayer metallization techniques. Pixel electrodes are formed at the intersections of the row and column lines. An active device such as a thin-film transistor (TFT) is formed at each pixel electrode to control the potential or current in the pixel electrode. A transparent conductive film is also formed on the second substrate. Both substrates are so arranged that the pixel electrodes on the first substrate are located opposite to the transparent conductive film on the second substrate.

In either type, the substrates are selected according to the used process. For example, the passive matrix construction needs no complex process steps except for steps where the transparent conductive films are formed and etched into row and column conducting line patterns. The substrates of this passive matrix type may be made from plastic, as well as from glass. On the other hand, to manufacture the active matrix construction, a relatively high-temperature film formation step is required. Furthermore, the active matrix type must keep out mobile ions such as sodium ions. The substrates of the active matrix type must be made of glass containing a quite low concentration of alkali.

In any type of prior art matrix display device excluding special constructions, a semiconductor integrated circuit (peripheral driver circuit) for driving the matrix is required to be mounted. In the past, this has been done by

00000000 15521560

tape automated bonding (TAB) or chip on glass (COG). However, the matrix construction contains as many as several hundreds of rows. Therefore, the integrated circuit has a very large number of terminals. The corresponding driver circuit takes the form of a rectangular IC package or semiconductor chip. To connect these terminals with the conducting lines on the substrates, it is necessary to lay the conducting lines in a complex manner. As a consequence, the ratio of the area of the peripheral portion, or non-display portion, to the area of the display portion is not negligibly small.

A method for solving this problem is disclosed in Japanese Patent Laid-Open No. 14880/1995, and consisting of forming a driver circuit on an elongated substrate (referred to as a stick or stick crystal) having a length substantially equal to one side of the matrix construction and connecting the driver circuit with the terminal portion of the matrix. This arrangement is permitted, because a width of about 2 mm suffices for the driver circuit. Therefore, almost the whole area of the substrate can be made a viewing screen.

Of course, in this case, where the matrix has a large area, it is impossible to form a circuit on a silicon wafer. Consequently, it is necessary to form the circuit on a glass substrate or the like. Hence, active devices used in semiconductor devices are TFTs.

However, where a stick crystal is employed, the thickness of the substrate of the driver circuit has been an obstacle to miniaturization of the whole display device. For example, where the display device should be made

thinner, the thickness of the substrate is allowed to be set to 0.3 mm by optimizing the kind of the substrate and the manufacturing steps. However, because of the strength necessary during manufacturing steps, it is difficult to reduce the thickness of the stick crystal below 0.5 mm. As a result, where two substrates are bonded together, the stick crystal protrudes as long as 0.2 mm or more.

Furthermore, if the stick crystal differs from the substrates of the display device in kind, then defects may be produced in the circuit because of the difference in coefficient of thermal expansion and for other causes. Especially, where a plastic substrate is used in a display device, this problem is conspicuous, because poor heat resistance of plastics makes it substantially impossible to use a plastic substrate as a stick crystal substrate.

Moreover, where the kind of the substrate supporting the stick crystal is different from the kind of the substrates of the display device, other known methods are used to circumvent the above-described problem. In one known method, a semiconductor integrated circuit having TFTs is fabricated on other support substrate. Then, the circuit is peeled off and adhesively bonded to another substrate. In another known method, the original support substrate is removed after adhesively bonding the circuit to another substrate. This technique is generally known as silicon-on-insulator (SOI) technique.

However, when the support substrate is removed, the semiconductor integrated circuit is often damaged, thus deteriorating the manufacturing yield.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide a smaller display device of reduced weight by solving the foregoing problems with the stick crystal.

It is another object of the invention to provide a method of fabricating display devices with a high production yield by solving the aforementioned problems.

The present invention is characterized in that the driver circuit portion of a display device is made thinner by mechanically bonding a semiconductor integrated circuit equivalent to a stick crystal to a substrate for the display device, making electrical connections, and then removing only the substrate from the stick crystal. In this construction, stress induced by deformation caused by thermal expansion of the substrate is applied uniformly to the whole circuit. Therefore, the stress is prevented from being concentrated in certain portions; otherwise it would be inevitable that defects are produced.

Essentially, the present invention lies in a display device comprising a first substrate and a second substrate having a transparent conductive film on its surface. Conducting lines are formed on the first substrate. The first substrate has an elongated semiconductor integrated circuit which is electrically connected with the conducting lines and has TFTs. The transparent conductive film on the second substrate faces the surface of the first substrate on which the conducting lines are formed. The length of the semiconductor integrated circuit is roughly equal to the length of one side of the viewing surface, or the matrix, of the display device, in the same way as the stick crystal

described in the above-cited Japanese Patent Laid-Open No. 14880/1995. The semiconductor integrated circuit is first fabricated on another substrate. The integrated circuit is peeled off and mounted on the first substrate.

In the case of the passive matrix type, the display device comprises a first substrate having an elongated first semiconductor circuit and a second substrate having a second semiconductor integrated circuit. A plurality of first conducting lines extending in a first direction are formed from a transparent conductive film on the first semiconductor integrated circuit. The first semiconductor integrated circuit is connected with the first conducting lines, has TFTs, and extends in a second direction substantially perpendicular to the first direction. The second substrate has second conducting lines which are formed from a transparent conductive film and extend in the second direction. The second semiconductor integrated circuit is connected with the second conducting lines, has TFTs, and extend in the first direction. The first and second substrates are so arranged that the first conducting lines are located opposite to the second conducting lines. The first and second semiconductor integrated circuits are obtained by fabricating them on other substrates, peeling the integrated circuits off, and bonding them to their respective substrates.

In the case of an active matrix type, the display device comprises a first substrate having a first and a second semiconductor integrated circuits and a second substrate having a transparent conductive film on its surface. A plurality of first conducting lines extending in a first

direction are formed on the first substrate. The first semiconductor integrated circuit is connected with the first conducting lines, has TFTs, and extend in a second direction substantially perpendicular to the first direction. A plurality of second conducting lines extending in the second direction are formed also on the first substrate. The second semiconductor integrated circuit is connected with the second conducting lines, has TFTs, and extends in the first direction. The first and second substrates are so arranged that the first and second conducting lines on the first substrate are opposite to the transparent conductive film on the second substrate. The first and second semiconductor integrated circuits are obtained by fabricating them on other substrates, peeling the integrated circuits off, and mounting them to the first substrate.

The method consisting of forming a semiconductor integrated circuit having TFTs on other substrate, peeling off the circuit, and bonding the circuit to a further substrate (alternatively, the original substrate is removed after bonding to another substrate) is generally known as one of SOI (silicon-on-insulator) techniques and described in Japanese Patent Laid-Open No. 504139/1994. Also, other well-known techniques can be used.

The step for peeling a semiconductor integrated circuit from its support substrate needs the most advanced technique. The present invention is characterized in that when the semiconductor integrated circuit is peeled from the support substrate, a gas containing a halogen, especially halogen fluoride, is used.

A halogen fluoride is given by a chemical formula XF_n ,

where X is a halogen other than fluorine and n is an integer. It is known that halogen fluorides include chlorine monofluoride (ClF), chlorine trifluoride (ClF₃), bromine monofluoride (BrF), bromine trifluoride (BrF₃), iodine monofluoride (IF), and iodine trifluoride (IF₃).

A halogen fluoride is characterized in that it etches silicon even under a non-plasma state but does not etch silicon oxide at all. Since it is not necessary to use a plasma, the circuit is not destroyed by plasma damage. This effectively contributes to an improvement in the production yield. Furthermore, the etching selectivity between silicon oxide and silicon is quite high. This is advantageous in that neither the circuit nor the elements are destroyed.

In the present invention, a peeling layer consisting principally of silicon is formed on a support substrate. A semiconductor integrated circuit coated with silicon oxide is formed on the peeling layer. As mentioned above, silicon is etched by a halogen fluoride without using a plasma. Other gases containing a halogen such as carbon tetrafluoride (CF₄) and nitrogen trifluoride (NF₃) etch silicon under a plasma condition and so they can be used for the invention.

Accordingly, by placing the support substrate either within a gas containing a halogen such as a halogen fluoride or within a plasma, the peeling layer is peeled from the support substrate. As a consequence, the semiconductor integrated circuit can be peeled off.

An example of a display device according to the present invention is shown in Figs. 1(A)-1(D) in cross section. Fig. 1(A) depicts the device with a relatively small

002020 112200

magnification. The left side of this figure shows a driver circuit portion 7 having a semiconductor integrated circuit 2. The right side shows a matrix portion 8. A conducting line pattern 4 is formed from a transparent conductive film on a substrate 1. A bump 6 is made of gold or other similar material. The semiconductor integrated circuit 2 has a thickness substantially equal to the thickness of TFTs. The integrated circuit 2 has a connector portion having an electrode 5 made of a conductive oxide whose contact resistance is not varied if it is oxidized. The electrode 5 is brought into contact with the bump 6. A resin 3 is injected between the semiconductor integrated circuit 2 and the substrate 1 to mechanically hold the components (Fig. 1(A)).

Fig. 1(B) is an enlarged view of the contact portion surrounded by the dotted line in Fig. 1(A). It is to be noted that like components are indicated by like reference numerals in various figures. Fig. 1(C) is an enlarged view of the portion surrounded by the dotted line in Fig. 1(B). The semiconductor integrated circuit includes an N-channel TFT 12 and a P-channel TFT 13 which are sandwiched by a buffer dielectric film 11 and an interlayer dielectric layer 14 and a passivation film 15 made of silicon nitride or the like (Figs. 1(B) and 1(C)).

When a semiconductor integrated circuit is formed, the buffer film 11 is normally made of silicon oxide. However, sufficient moisture resistance cannot be obtained only with this scheme. Therefore, a passivation film must be formed on the buffer film. If the semiconductor circuit and its contact portion are thinner than the spacing between the

substrates of the device as shown in Fig. 3, then it is possible to form a counter substrate 16 on the circuit. In this case, the outer side of the driver circuit portion 7 is sealed with a sealing material 17 such as epoxy resin, in the same way as the manufacture of a liquid crystal device as disclosed in Japanese Patent Laid-Open No. 66413/1993. The gap between the substrates 1 and 16 is filled with a liquid crystal material 18 and so mobile ions do not intrude into the gap from the outside. Hence, any special passivation film is not required (Fig. 3).

The contact portion can use a bump as described above. Another method is illustrated in Fig. 1(D). That is, conductive particles 9 such as particles of gold are diffused into the contact portion to provide electrical contact. The diameter of the particles is slightly greater than the spacing between the semiconductor integrated circuit 2 and the substrate 1 (Fig. 1(D)).

The sequence for fabricating this display device which is of the passive matrix type is shown in Figs. 2(A)-2(G). First, a number of semiconductor integrated circuits 22 are formed on an appropriate substrate 21 (Fig. 2(A)).

The resulting laminate is cut to form stick crystals 23 and 24. The electrical characteristics of the obtained stick crystals 23 and 24 may be checked before the next manufacturing step is effected, to judge whether the crystals are acceptable or rejected (Fig. 2(B)).

Then, the surfaces of the stick crystals 23 and 24 on which the circuits are formed are bonded to surfaces 26 and 28 of separate substrates 25 and 27, respectively. Conducting line patterns are formed from transparent

conductive films on the surfaces 26 and 28. Electrical connections are made (Figs. 2(C) and 2(D)).

Subsequently, the stick drivers 23 and 24 are peeled from their respective substrates by SOI techniques or by processing with a gas containing a halogen. In this way, only semiconductor integrated circuits 29 and 30 are left on the surfaces 26 and 28, respectively, of the substrates (Figs. 2(E) and 2(F)).

Finally, the laminates obtained in this manner are made to face each other. As a result, a passive matrix display is derived. A surface 26 faces away from the surface 26. That is, no conducting line pattern is formed on the surface 26 (Fig. 2(G)).

In the above example, the row stick crystal (i.e., the stick crystal for a driver circuit for driving row lines) and the column stick crystal (i.e., the stick crystal for a driver circuit for driving column lines) are extracted from the same substrate 21. Of course, they may be extracted from separate substrates.

The example shown in Figs. 2(A)-2(G) is a passive matrix display. Obviously, the invention can be similarly applied to an active matrix display. In the illustrated examples given below, each substrate is made of a filmy material.

Other objects and features of the invention will appear in the course of the description thereof, which follows.

BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1(A)-1(D) are cross-sectional views of a display device according to the present invention;

Figs. 2(A)-2(G) are exploded perspective views of

another display device according to the invention, schematically illustrating a method of fabricating the device;

Fig. 3 is a cross-sectional view of a further display device according to the invention;

Figs. 4(A)-4(C) are cross-sectional views of a stick crystal used for manufacturing steps according to the invention;

Figs. 5(A)-5(D) are cross-sectional views, illustrating steps for bonding a stick crystal to a substrate; and

Fig. 6 is a schematic view of a system for fabricating filmy liquid crystal devices in succession.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

EXAMPLE 1

Manufacturing steps for fabricating one substrate of a passive matrix liquid crystal display are briefly described now. The present example is described by referring to Figs. 4(A)-4(C) and 5(A)-5(D). Steps for forming a driver circuit on a stick crystal are schematically shown in Figs. 4(A)-4(C). Steps for mounting the stick crystal on the substrate of the liquid crystal display are schematically shown in Figs. 5(A)-5(D).

First, a silicon film having a thickness of 3000Å was deposited as a peeling layer 32 on a glass substrate 31. Since the silicon film becoming the peeling layer 32 is etched away when circuitry and a substrate formed on the silicon film are separated, the quality of the silicon film will present almost no problems. Therefore, the silicon film may be deposited by a method which permits mass

production. Furthermore, the silicon film may be either amorphous or crystalline in character.

The glass substrate may be made of Corning 7059 glass, Corning 1737 glass, NH Technoglass NA45, NH Technoglass NA35, Nippon Denki Glass OA2, other non-alkali or low-alkali glass, or quartz glass. Where quartz glass is used, the cost poses a problem. In the present invention, however, the area of the substrate used in one liquid crystal display is quite small and so the cost per device is sufficiently low.

A silicon oxide film was deposited as a buffer film 33 having a thickness of 5000Å on the peeling layer 32. Sufficient care must be taken in fabricating the buffer film 33 from silicon oxide. Islands 34 and 35 of crystalline silicon region were formed by a well-known method. The thickness of the islands of crystalline silicon region greatly affects the required semiconductor characteristics. Generally, it was desired to make the thickness smaller. In the present example, the thickness was 400-600Å.

Where crystalline silicon is obtained, laser annealing (i.e., amorphous silicon is illuminated with intense light such as laser light) or solid-phase epitaxy using thermal annealing is employed. Where solid-phase epitaxy is utilized, if a catalytic element such as nickel is added to the silicon as disclosed in Japanese Patent Laid-Open No. 244104/1994, then the crystallization temperature can be lowered, and the annealing time can be shortened. Furthermore, as described in Japanese Patent Laid-Open No. 318701/1994, once silicon is crystallized by solid-phase epitaxy, it may be laser-annealed. The adopted method is

determined, taking account of the required semiconductor circuit characteristics, the maximum processing temperature of the substrate, and other factors.

Then, a gate-insulating film 36 of silicon oxide having a thickness of 1200Å was deposited by plasma CVD or thermal CVD. Subsequently, gate electrodes/interconnects 37, 38 were formed from a crystalline silicon film having a thickness of 5000Å. The gate electrodes/interconnects 37, 38 may be made from metals such as aluminum, tungsten, and titanium, or their silicides. Where metallic gate electrodes/interconnects 37, 38 are formed, their top or side surfaces may be coated with anodic oxide as disclosed in Japanese Patent Laid-Open Nos. 267667/1993 and 338612/1994. The material of the gate electrodes/interconnects 37, 38 is determined according to the required semiconductor circuit characteristics, the maximum processing temperature of the substrate, and other factors (Fig. 4(A)).

Thereafter, N- and P-type impurity ions were introduced into the islands of silicon 34 and 35 by self-aligned ion implantation or other method to form N-type regions 39 and P-type regions 40. Then, an interlayer dielectric film 41 of silicon oxide having a thickness of 5000 Å was deposited by a well-known means. Contact holes were created in this interlayer dielectric film. Aluminum alloy interconnects 41-44 were formed (Fig. 4(B)).

A silicon nitride film 46 having a thickness of 2000Å was deposited as a passivation film on the laminate by plasma CVD. Contact holes communicating with the output terminal lines 44 were formed in this passivation film. An

ITO (indium-tin oxide) electrode 47 having a thickness of 1000Å was formed by sputtering techniques. ITO is a transparent conductive oxide. A gold bump 48 having a diameter of about 50µm and a height of 30µm was mechanically formed on the ITO electrode 47. The resulting circuit was cut into appropriate size, thus obtaining a stick crystal (Fig. 4(C)).

An electrode 50 was formed also from ITO to a thickness of 1000Å on another substrate 49 of the liquid crystal display. In the present example, a substrate of polyethylene sulfite having a thickness of 0.3 mm was used. The substrate 31 of the stick driver was bonded to this substrate 49 under pressure. At this time, the electrodes 47 and 50 were electrically connected to each other via the bump 48 (Fig. 5(A)).

Then, an adhesive 51 to which a thermosetting organic resin was added was injected into the gap between the stick crystal 31 and the substrate 49 of the liquid crystal display. The adhesive may be applied to the surface of any one of the stick crystal 31 and the substrate 49 before they are bonded together under pressure.

The laminate was processed for 15 minutes in an oven filled with a nitrogen ambient at 120°C. In this way, electrical connection and mechanical bonding between the stick crystal 31 and the substrate 49 were completed. Before the bonding operation is completed in this way, a check may be done to see whether the electrical connection is satisfactory or not by the method disclosed in the above-cited Japanese Patent Laid-Open No. 14880/1995 (Fig. 5(B)).

The laminate processed in this way was allowed to stand

in a stream of mixture gas of chlorine trifluoride (ClF_3) and nitrogen. The flow rate of each of the chlorine trifluoride and nitrogen was 500 SCCM. The reaction pressure was 1 to 10 torr. The temperature was room temperature. It is known that halogenated fluorine such as chlorine trifluoride selectively etches silicon. On the other hand, oxides such as silicon oxide and ITO are hardly etched. Also with respect to aluminum, if a stable oxide coating is formed on an aluminum film, then reaction no longer progresses. Hence, the aluminum is not etched.

In the present example, materials which might be attacked by chlorine trifluoride are the peeling layer (silicon) 32, the islands of silicon 34, 35, the gate electrodes/interconnects 37, 38, the aluminum alloy interconnects 41-44, and the adhesive 51. These materials excluding the peeling layer 32 and the adhesive 51 are capped with silicon oxide and other materials and, therefore, chlorine trifluoride is unable to reach them. In practice, only the peeling layer 32 was selectively etched as shown in Fig. 5(C), thus forming voids 52.

As time passed further, the peeling layer 32 was completely etched away, so that the bottom surface 53 of the buffer film 33 was exposed. Thus, the substrate 31 of the stick crystal was separated from the semiconductor circuit. With etching using chlorine trifluoride, the etching process came to a stop at the bottom surface of the buffer film and so the bottom surface 53 was quite flat (Fig. 5(D)).

In this manner, fabrication of the semiconductor integrated circuit on one substrate of the liquid crystal display was completed. The liquid crystal display is

completed, using the substrate obtained in this way.

EXAMPLE 2

The present example relates to a method (referred to as the roll-to-roll method) of successively fabricating filmy passive matrix liquid crystal displays. A production system for implementing the present example is shown in Fig. 6. The substrate material for obtaining the filmy liquid crystal displays may be selected from polyethylene sulfite, poly-carbonate, and polyimide. Since polyethylene terephthalate and polyethylene naphthalate are polycrystalline plastics, they are not appropriate as liquid crystal materials which provide displays making use of polarization of light.

The production system shown in Fig. 6 is divided into two major parts: the upper portion and the lower portion. In the lower portion, a substrate on which color filters are formed is fabricated as a component of a liquid crystal display. In the upper portion, a counter substrate is manufactured. First, steps for fabricating the substrate on which the color filters are formed are described.

Color filters of the three primary colors (RGB) are printed on the surface of a film wound on a roll 71. The color filters are formed, using three sets of rolls 72. Where the manufactured liquid crystal displays are monochrome devices, this step is dispensed with. This step is referred to as color filter printing.

Then, an overcoat is printed to form a planarization film, using rolls 73. The overcoat acts to planarize the surface which is made uneven by the formation of the color

filters. A transparent resinous material may be used as the material of the overcoat. This step is referred to as printing of overcoat (planarization film).

Then, row (column) electrodes are printed in a desired pattern, using a conductive ink, by means of rolls 74. This step is referred to as formation of electrodes.

Thereafter, an orientation film is printed, using rolls 75. This step is referred to as printing of orientation film. The film is passed through a heating furnace 76 to bake and solidify the orientation film. This step is referred to as the baking of orientation film.

The film is then passed between rolls 77 to rub the surface of the orientation film. In this way, the orientation step is completed. This step is referred to as rubbing.

Then, a stick crystal is mounted on the substrate by a pressure connection device 78. This step is referred to as mounting of the stick crystal. The laminate is passed through a heating furnace 79 to cure the adhesive. Thus, the bonding operation is completed. This step is referred to as curing of the adhesive.

In the present example, the peeling layer uses silicon, in the same way as in Example 1. Then, the peeling layer is etched by a chlorine trifluoride chamber 80 which is differentially pumped to prevent the chlorine trifluoride from leaking out. As a result, the substrate is peeled from the stick crystal. This step is referred to as peeling of the stick crystal.

Then, spacers are sprayed onto the filmy substrate by a spacer applicator 81. This step is referred to as spraying

of spacers. A sealing material is printed, using rolls 82. The sealing material acts to bond together the two opposite substrates and to prevent the liquid crystal material from leaking from the space between the substrates. In the present example, the semiconductor circuit is rendered thinner than the spacing between the substrates to seal the outer surface of the semiconductor integrated circuit as shown in Fig. 3, as disclosed in the above-cited Japanese Patent Laid-Open No. 66413/1993. This step is referred to as printing of the sealant.

Subsequently, a liquid crystal material is dripped, using a liquid crystal dripper 83. As a result, a liquid crystal material layer is formed on the filmy substrate. In this way, the substrate on the side of the color filters, or a color filter panel, is completed. These manufacturing steps are made to progress successively by rotating the various rolls.

Then, steps for manufacturing the counter substrate are described. Column (row) electrodes are formed in a desired pattern on the filmy substrate fed out of a roll 61 by means of rolls 62. This step is referred to as formation of electrodes.

Thereafter, an orientation film is formed by printing techniques, using rolls 63. This step is referred to as printing of the orientation film. The film is passed through a heating furnace 64 to bake and solidify the orientation film. This step is referred to as baking of the orientation film.

Then, the filmy substrate is passed between rolls 65 to orient the molecules of the liquid crystal material. This

step is referred to as rubbing.

The stick crystal is mounted on the substrate by a pressure connection device 66. This step is referred to mounting of the stick crystal. The laminate is passed through a heating furnace 67 to cure the adhesive. This step is referred to as curing of the adhesive.

Then, the substrate of the stick crystal is peeled off by a chlorine trifluoride chamber 68. This step is referred to as peeling of the stick crystal.

The filmy substrate undergone the steps described thus far is passed around a roll 69 and sent to next rolls 84. The substrate having the color filters and the counter substrate are bonded together by the rolls 84, thus forming a liquid crystal cell. This step is referred to as bonding.

The assembly is then heated by a heating furnace 85 to cure the sealing material. In this way, the bonding of the substrates is completed. This step is referred to as curing of the sealant.

The assembly is cut into desired dimensions by a cutter 86, thus completing a filmy liquid crystal display. This step is referred to as cutting.

In the present invention, the kinds, the thickness, and the size of the substrates of the display device can be varied variously. For example, as described in Example 2, a liquid crystal display in the form of a quite thin film can be obtained. In this case, the display device may be curved along a curved surface and bonded to it. Furthermore, less restrictions are imposed on the kind of the substrates. As a consequence, a lightweight material having high shock resistance such as a plastic substrate may also be used.

This improves the portability.

In addition, in the present invention, the semiconductor integrated circuit forming a driver circuit is peeled from its support substrate by a halogen-containing gas which is not in a plasma state. Therefore, destruction of the semiconductor integrated circuit which would normally be caused by plasma damage can be prevented. This leads to an improvement in the yield with which liquid crystal displays are manufactured.

Moreover, the driver circuit occupies less area and so the display device can be arranged relative to other devices with a greater degree of freedom. Typically, the driver circuit can be confined within a region only a few centimeters wide around the display surface. Therefore, the display device itself is quite simple and is a highly fashionable industrial product. It can find extensive application. Hence, the present invention is industrially quite advantageous.

What is claimed is:

1. A method of manufacturing an active matrix display device wherein said display device has a first substrate provided with a plurality of pixel electrodes and switching thin film transistors, the method comprising the steps of:

forming a semiconductor film over a glass substrate;
crystallizing said semiconductor film;
patterning the crystallized semiconductor film into a plurality of semiconductor islands;
forming a plurality of thin film transistors using said semiconductor islands;
forming a driver circuit with said plurality of thin film transistors;
attaching said glass substrate provided with said driver circuit to said first substrate.

2. A method of manufacturing a display device comprising:

preparing at least one display substrate provided with electrodes;
forming a semiconductor film over a glass substrate;
crystallizing said semiconductor film;

patterning the crystallized semiconductor film into a plurality of semiconductor islands;

forming a plurality of thin film transistors with said semiconductor islands for constituting a plurality of driver circuits;

dividing said glass substrate to obtain at least one divided glass substrate wherein said divided glass substrate carries at least one of said driver circuits thereon; and

attaching said divided glass substrate to a display substrate so that said driver circuit is electrically connected to said electrodes.

3. A method according to claim 2 wherein said display device is a passive type liquid crystal device.

4. A method according to claim 2 wherein said display device is an active matrix type liquid crystal device.

5. A method according to claim 2 further comprising a step of removing the divided glass substrate from said display substrate.

6. A method of manufacturing a display device comprising:

preparing at least one display substrate provided with electrodes wherein said display substrate comprises a plastic;

forming a semiconductor film over a glass substrate;
crystallizing said semiconductor film;

patterning the crystallized semiconductor film into a plurality of semiconductor islands;

forming a plurality of thin film transistors with said semiconductor islands as an active layer thereof for constituting a plurality of driver circuits;

dividing said glass substrate to obtain at least one divided glass substrate wherein said divided glass substrate carries at least one of said driver circuits thereon; and

attaching said divided glass substrate to a display substrate so that said driver circuit is electrically connected to said electrodes.

7. A method according to claim 6 wherein said display device is a passive type liquid crystal device.

8. A method according to claim 6 further comprising a step of removing the divided glass substrate from said display substrate.

9. A method of manufacturing an active matrix type display device comprising:

preparing at least one display substrate provided with a plurality of pixel electrodes and switching thin film transistors for switching said pixel electrodes;

forming a semiconductor film over a glass substrate;

crystallizing said semiconductor film;

patterning the crystallized semiconductor film into a plurality of semiconductor islands;

forming a plurality of thin film transistors with said semiconductor islands as an active layer thereof for constituting a plurality of driver circuits;

dividing said glass substrate to obtain at least one divided glass substrate wherein said divided glass substrate carries at least one of said driver circuits thereon; and

attaching said divided glass substrate to a display substrate so that said driver circuit is operationally connected to said switching thin film transistors.

10. A method according to claim 9 further comprising a step of removing the divided glass substrate from said display substrate.

11. A method according to claim 9 wherein a thickness of said semiconductor islands is from 400 to 600Å.

12. A method of manufacturing an active matrix type display device comprising:

preparing at least one display substrate provided with a plurality of pixel electrodes and switching thin film transistors for switching said pixel electrodes

forming a semiconductor film over a glass substrate;

crystallizing said semiconductor film wherein the crystallization is promoted by adding a catalyst to said semiconductor film;

patterning the crystallized semiconductor film into a plurality of semiconductor islands;

forming a plurality of thin film transistors with said semiconductor islands as an active layer thereof for constituting a plurality of driver circuits;

dividing said glass substrate to obtain at least one divided glass substrate wherein said divided glass

substrate carries at least one of said driver circuits thereon; and

attaching said divided glass substrate to a display substrate so that said driver circuit is operationally connected to said switching thin film transistors.

13. A method according to claim 12 further comprising a step of removing the divided glass substrate from said display substrate.

14. A method according to claim 12 wherein a thickness of said semiconductor islands is from 400 to 600Å.

15. A method according to claim 12 wherein said catalyst comprises nickel.

16. A method of manufacturing a display device comprising:

preparing at least one display substrate provided with a plurality of first electrodes;

forming a semiconductor film over a glass substrate;

crystallizing said semiconductor film;

patterning the crystallized semiconductor film into a plurality of semiconductor islands;

forming a plurality of thin film transistors with said semiconductor islands as an active layer thereof for constituting a plurality of driver circuits;

forming a passivation film over the plurality of thin film transistors;

forming transparent electrodes over said passivation film wherein said transparent electrodes comprise a transparent conductive oxide;

dividing said glass substrate to obtain at least one divided glass substrate wherein said divided glass substrate carries at least one of said driver circuits thereon; and

attaching said divided glass substrate to a display substrate so that said driver circuit is electrically connected to said first electrodes through said transparent electrodes.

17. A method according to claim 16 further comprising a step of removing the divided glass substrate from said display substrate.

18. A method according to claim 16 wherein a thickness of said semiconductor islands is from 400 to 600Å.

19. A method according to claim 16 wherein said passivation film comprises silicon nitride.

20. A method according to claim 16 wherein said display device is a passive type liquid crystal device.

21. A method according to claim 16 wherein said display device is an active matrix type liquid crystal device.

22. A method of manufacturing a display device comprising:

preparing at least one display substrate provided with a plurality of first transparent electrodes;

forming a semiconductor film over a glass substrate;
crystallizing said semiconductor film;

patterning the crystallized semiconductor film into a plurality of semiconductor islands;

forming a plurality of thin film transistors with said semiconductor islands as an active layer thereof for constituting a plurality of driver circuits;

forming a passivation film over the plurality of thin film transistors;

forming second transparent electrodes over said passivation film wherein said transparent electrodes comprise a transparent conductive oxide;

dividing said glass substrate to obtain at least one divided glass substrate wherein said divided glass substrate carries at least one of said driver circuits thereon; and

attaching said divided glass substrate to a display substrate so that said driver circuit is electrically connected to said electrodes through said first and second transparent electrodes.

23. A method according to claim 22 wherein a thickness of said semiconductor islands is from 400 to 600Å.

24. A method according to claim 22 wherein said display device is a passive type liquid crystal device.

25. A method according to claim 22 further comprising a step of removing the divided glass substrate from said display substrate so that said driver circuit remains connected to said electrodes.

26. A method according to claim 22 wherein said display device is a passive type liquid crystal device.

27. A method according to claim 22 wherein said display device is an active matrix type liquid crystal device.

10020949.doc

ABSTRACT OF THE DISCLOSURE

A method of fabricating a driver circuit for use with a passive matrix or active matrix electrooptical display device such as a liquid crystal display. The driver circuit occupies less space than heretofore. A circuit (stick crystal) having a length substantially equal to the length of one side of the matrix of the display device is used as the driver circuit. The circuit is bonded to one substrate of the display device, and then the terminals of the circuit are connected with the terminals of the display device. Subsequently, the substrate of the driver circuit is removed. This makes the configuration of the circuit much simpler than the configuration of the circuit heretofore required by the TAB method or COG method, because conducting lines are not laid in a complex manner. The driver circuit can be formed on a large-area substrate such as a glass substrate. The display device can be formed on a lightweight material having a high shock resistance such as a plastic substrate. Hence, a display device having excellent portability can be obtained.




Figure 1A




Figure 1B




Figure 1C











Figure 1D








Figure 5A




Figure 5B




Figure 5C





Figure 5D



COMBINED DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

DISPLAY DEVICE AND METHOD OF FABRICATING THE SAME

the specification of which

☒ is attached hereto.

☐ was filed on _____ as Application Serial No. _____

— and was amended on _____.

☐ was described and claimed in PCT International Application No. _____

filed on _____ and as amended under PCT Article 19 on _____.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose all information I know to be material to patentability in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

COUNTRY	APPLICATION NO.	FILING DATE	PRIORITY CLAIMED
JAPAN	7-86457	03/16/1995	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
JAPAN	7-79708	03/10/1995	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
_____	_____	_____	<input type="checkbox"/> Yes <input type="checkbox"/> No
_____	_____	_____	<input type="checkbox"/> Yes <input type="checkbox"/> No

I hereby appoint the following attorneys and/or agents to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith: Scott C. Harris Reg. No. 32,030; William E. Booth, Reg. No. 28,933; Barry E. Bretschneider, Reg. No. 28,055; John W. Freeman, Reg. No. 29,066; Timothy A. French, Reg. No. 30,175; Alan H. Gordon, Reg. No. 26,168; John F. Land, Reg. No. 29,554; John B. Pegram, Reg. No. 25,198; Rene D. Tegtmeyer, Reg. No. 33,567; Hans R. Troesch, Reg. No. 36,950; Dorothy P. Whelan, Reg. No. 33,814; Charles C. Winchester, Reg. No. 21,040.

Address all telephone calls to Scott C. Harris at telephone number 202/783-5070.

Address all correspondence to Scott C. Harris, Fish & Richardson P.C., 601 13th Street NW, Washington, D.C. 20005.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patents issued thereon.

Full Name of Inventor: Shunpei YAMAZAKI

Inventor's Signature: *Shunpei Yamazaki* Date: February 29, 1996

Residence Address: Tokyo, Japan

COMBINED DECLARATION AND POWER OF ATTORNEY CONTINUED

Citizen of: Japanese

Post Office Address: 4-10-20, Seijo, Setagaya-ku, Tokyo 157 Japan

Full Name of Inventor: Yasuhiko TAKEMURA


Inventor's Signature:  Date: February 29, 1996

Residence Address: Kanagawa, Japan

Citizen of: Japanese

Post Office Address: San White Harashima 202, 934-3, Aiko, Atsugi-shi, Kanagawa-ken 243 Japan

Full Name of Inventor: Setsuo NAKAJIMA


Inventor's Signature:  Date: February 29, 1996

Residence Address: Kanagawa, Japan

Citizen of: Japanese

Post Office Address: Flat Atsugi 306, 931-1, Hase, Atsugi-shi, Kanagawa-ken 243 Japan

Full Name of Inventor: Yasuyuki ARAI

Inventor's Signature:  Date: February 29, 1996

Residence Address: Kanagawa, Japan

Citizen of: Japanese

Post Office Address: 1-29-6-202, Morinosato, Atsugi-shi, Kanagawa-ken 243-01 Japan